Check for updates

METHOD ARTICLE

Numerical model for enhancing stimulated Brillouin scattering in optical microfibers [version 1; peer review: 1 approved, 1 approved with reservations]

Soon Heng Yeap^{1,2}, Siamak Dawazdah Emami^{1,3}, Hairul Azhar Abdul-Rashid ¹

¹Fiber Optics Research Center, Multimedia University, Cyberjaya, Selangor, 63100, Malaysia

²Research Department, Broadcom, Bayan Lepas, Penang, 87300, Malaysia

³Laser and Plasma Research Institute, Shahid Beheshti University, Evin, Tehran, Iran

V1 First published: 30 Jun 2021, 10:521
<https://doi.org/10.12688/f1000research.51029.1>

Latest published: 17 Feb 2022, 10:521
<https://doi.org/10.12688/f1000research.51029.2>

Abstract

Stimulated Brillouin scattering (SBS) is useful, among others for generating slow light, sensing and amplification. SBS was previously viewed as a poor method due to the limitation on optical power in high-powered photonic applications. However, considering the many possible applications using SBS, it is now of interest to enhance SBS in areas of Brillouin frequency shift together with Brillouin Gain. A numerical model, using a fully vectorial approach, by employing the finite element method, was developed to investigate methods for enhancing SBS in optical fiber. This paper describes the method related to the numerical model and discusses the analysis between the interactions of horizontal, shear and hybrid acoustic modes; and optical modes in optical fiber. Two case studies were used to demonstrate this. Based on this numerical model, we report the influence of core radius, clad radius and effective refractive index on the Brillouin frequency shift and gain. We observe the difference of Brillouin shift frequency between a normal silica optical fiber and that of a tapered fiber where nonlinearities are higher. Also observed, the different core radii used and their respective Brillouin shift. For future work, the COMSOL model can also be used for the following areas of research, including simulating “surface Brillouin shift” and also to provide in-sights to the Brillouin shift frequency vB of various structures of waveguides, e.g circular, and triangular, and also to examine specialty fibers, e.g. Thulium and Chalcogenide doped fibers, and their effects on Brillouin shift frequency.

Keywords

Stimulated Brillouin Scattering, Brillouin Shift Frequency, Effective Refractive Index, COMSOL, Slow Light

Open Peer Review

Approval Status

1

2

version 2

(revision)

17 Feb 2022

version 1

30 Jun 2021

[view](#)

[view](#)

1. **Gand Ding Peng** , University of New South Wales, Sydney, Australia

2. **Ahmad Ashrif A Bakar** , Universiti Kebangsaan Malaysia, Bangi, Malaysia
 Universiti Kebangsaan, Kuala Lumpur, Malaysia

Any reports and responses or comments on the article can be found at the end of the article.

This article is included in the **Research Synergy**
Foundation gateway.

Corresponding author: Hairul Azhar Abdul-Rashid (hairul@mmu.edu.my)

Author roles: **Yeap SH:** Formal Analysis, Investigation, Methodology, Writing – Original Draft Preparation; **Emami SD:** Conceptualization, Resources, Software, Validation, Visualization, Writing – Original Draft Preparation; **Abdul-Rashid HA:** Conceptualization, Formal Analysis, Project Administration, Resources, Supervision, Writing – Review & Editing

Competing interests: No competing interests were disclosed.

Grant information: This work was supported by Telekom Malaysia Berhad.

The funders had no role in study design, data collection and analysis, decision to publish, or preparation of the manuscript.

Copyright: © 2021 Yeap SH *et al.* This is an open access article distributed under the terms of the **Creative Commons Attribution License**, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

How to cite this article: Yeap SH, Emami SD and Abdul-Rashid HA. **Numerical model for enhancing stimulated Brillouin scattering in optical microfibers [version 1; peer review: 1 approved, 1 approved with reservations]** F1000Research 2021, 10:521
<https://doi.org/10.12688/f1000research.51029.1>

First published: 30 Jun 2021, 10:521 <https://doi.org/10.12688/f1000research.51029.1>

Introduction

Stimulated Brillouin scattering (SBS) is a nonlinear process caused by acoustic phonon scattering propagating in the backward direction. Acoustic vibration across mediums scatters the incident light of the pump wave causing an acoustic frequency shift resulting in Stokes and anti-Stokes waves. The process of transferring energy from the pump wave to the Stokes wave is known as the scattering phenomenon. The Stokes wave counter propagates in the opposite direction to the pump wave. The presence of acoustic waves propagating on the medium's surface is known as the surface acoustic wave. SBS theory was first explained by Leon Brillouin in 1922, and since then related experimental works have been performed in the past decade.¹ This paper describes a numerical model that analyzes the interactions of horizontal, shear and hybrid acoustic modes; and optical modes in optical fibers. The numerical model was developed using COMSOL Multiphysics. Two case studies were used to demonstrate the model's utility. Based on this numerical model, we report the influence of core radius, clad radius and effective refractive index on the Brillouin frequency shift and gain coefficient.

Literature review

Prior studies related to SBS have focused on the acoustic frequency shift of different types of fibers. In theory, peak Brillouin gain for a standard silica fiber is approximated to be 5×10^{-11} m/W.² In addition, fibers around 2.6×10^{-12} m/W have been presented by Nikles *et al.*³ Optimized SBS acoustic frequency shift for tellurite photonic crystal fiber (PCF) was recorded at 8.43 GHz, which gives 9.48×10^{-11} m/W of Brillouin gain.⁴ Experimental results for SBS across a chalcogenide fiber was demonstrated by Song *et al.* at 6.08×10^{-9} m/W, showing a higher Brillouin gain compared to a standard silica fiber.⁵ Woodward *et al.* reported an experimental study on SBS in small-core PCF,⁶ which discussed the complexity of acoustic wave dynamics for different wavelengths of light, overlap between optical waves were minimum at 532 nm. Consequently, at 1550 nm, a higher overlap is achieved, which contributes to a higher Brillouin gain, and therefore a lower threshold power of 1160 mW.⁶ More recently, Tchahame *et al.* demonstrated a multimode Brillouin spectrum across a long tapered PCF.⁷ Beugnot *et al.* successfully conducted both the first numerical and experimental work on surface acoustic waves (SAW) of silica microfiber in 2014, with a Brillouin gain equivalent to 1.4×10^{-12} m/W.⁸ The idea is greatly appreciated as SAW has outstanding potential contribution in the optical sensor due to its sensitivity on various physical perturbations. However, the limitation is that threshold power of the tapered fiber is relatively high and so it is not feasible in optical application. Acoustic confinement in the fiber core is required to ensure high overlap with the optic wave. Cherif *et al.* studied the Brillouin spectrum of SBS characterization for small core tellurite PCF with variation in air-filling ratio.⁴ In addition, previous results by Hu *et al.* showed a low threshold power of 52 mW on chalcogenide fibers whose acoustic waves were confined to the core.⁹ However, for SBS across tapered silica fibers an undesired high threshold power was observed due to a reduced interaction of the surface acoustic wave with the optical wave. To counter this effect, gold and silver cladding materials have been proposed. The finding from Kim *et al.* shows novel shear Brillouin scattering detection using microscopic resolution.¹⁰ This finding is fundamental as previous experimental set ups focused on longitudinal acoustic wave propagation.

Several experimental studies have been carried out by researchers to study the behavior of SBS in optical fibers. However, there are several limitations in experimental studies such as fabrication certainty, environmental influences and access to laboratory equipment. An accurate modeling tool, developed for the purpose of aiding experimental studies, would be beneficial to speed up research while preserving a good level of accuracy and confidence. Finite Element Method (FEM), a method that applies meshing technique to solve partial differential equations (PDE) with a certain boundary condition.¹⁴ FEM received great attention when improvements in handling boundary conditions with the implication of penalty functions was discussed.¹⁵ This gave FEM the preference in optical fiber modeling considering the boundary issue as the problem that other methods fail in. Ham *et al.*¹⁶ then introduced the complete numerical solution, where FEM is used with spectral method that provides accuracy and consistency for 2-D and 3-D cases involving harmonic functions. These findings made FEM more suitable for optical fiber numerical modeling. Sriratanavaree *et al.*¹⁷ used FEM in the study of optical and acoustic wave interaction in silicon slot waveguides. Subsequently, Monfared *et al.*¹⁸ showed how FEM modeled for composite behavior of bond particle at fiber interface. Findings from Liu *et al.*¹⁹ showed a numerical solution using FEM to enumerate the tension and bending in optical fiber accurately. A report on optical fiber modeling and simulation of effective refractive index for tapered fiber with finite element method was deliberated by Lee *et al.*²⁰ Rahman *et al.*^{11, 12} reported numerical modeling of SBS, considering the optical fundamental mode in the optical fiber using FEM.

Methods

We present a numerical model to optimize Brillouin frequency shift and gain based on various core diameters of the tapered region of silica microfiber structures. To further understand the interactions, the COMSOL model should be capable of modelling solutions in the given structures of the optical fiber. Previous research was mainly done to enhance performance on spatial resolution and also sensing range, but there have not been many insights for gain. The ability to increase the Brillouin gain coefficient has opened new opportunities to control their interaction, and several new

industrial and commercial applications. In this research work, we demonstrate the numerical model for a microfiber design that is expected to increase Brillouin gain coefficient. The fully vectorial method, developed in COMSOL, is used in this case to determine the contributions of various optical fibre parameters towards SBS, thus aiding the design of microfibers with enhanced SBS performance. The equation below is used for the analysis of light guidance where H is the full vectorial magnetic field, $*$ represents the complex conjugate and transpose, ω^2 denotes the eigenvalue where ω is the optical angular frequency of the wave and ϵ and μ are the permittivity and permeability, respectively.²¹

$$\omega^2 = \frac{\int ((\nabla \times H)^* \cdot \epsilon^{-1} (\nabla \times H) + \rho (\nabla \cdot H)^* (\nabla \cdot H)) dx dy}{\int H^* \mu H dx dy} \quad (1)$$

Equation (1) solves for the propagation constant of optical modes in optical waveguides, which can also guide acoustic mode. The propagation constant of the optical wave, β , is defined as $\beta_{\text{optic}} = 2\pi n_{\text{eff}}/\lambda$. There are two basic types of acoustic waves, namely shear and longitudinal acoustic waves. Shear waves are associated with dominant material dispersion in the transverse directions, which is perpendicular to the direction of propagation, taken here as the z-axis. On the other hand, for a longitudinal wave, expansion and contraction of the wave is associated with particle movements along the z direction which is in parallel to the wave propagation. However, acoustic wave propagating through a waveguide can be a combination of shear and longitudinal acoustic waves. Brillouin frequency shift of the Stokes wave is given as $f = 2n_{\text{eff}} V_{\text{ac}}/\lambda$, where, V_{ac} is the acoustic velocity. The acoustic wave satisfies Hooke's Law¹² which relates to the stress (tensor) and strain (force) of the waveguiding materials. Electric field associated with a high power optical signal causes molecular movements due to electrostriction process.¹³ Such a material movement can generate acoustic waves that leads to density variation along the waveguide. The time and space dependent density variation changes the refractive index profile and produces a moving optical grating. This grating can reflect incoming light when its wavelength matches the spatial period of the gratings generated by the acoustic wave. Above a threshold power, if phase matching conditions are satisfied, it can inhibit forward guidance of the incoming light. The backward scattered reflected wave is frequency shifted, which explains the occurrence of the Stokes Wave. The relationship between optic and acoustic propagation for phase matching condition can be given as: $K_{\text{acoustic}} = 2\beta_{\text{optic}}$ where K_{acoustic} is the acoustic propagation constant and this will be double of the β_{optics} the optic propagation constant.

For the SBS characterization in the optical fiber, both its guided optical and acoustic modes can be obtained using the FEM. The n_{eff} for the optical mode in a fibre for a given radius is first calculated using H-field based FEM model. Eigenvector and eigenvalue of acoustic waves are also obtained and then the acoustic mode patterns are generated. At phase matched conditions, the acoustic wave propagation constant is double the value of the optical wave propagation constant: $K_{\text{acoustic}} = 2\beta_{\text{optic}}$.

In this research work, the fully vectorial approach was used to solve the optical wave equations for n_{eff} using the commercial COMSOL software. The optical parameters $E(x,y)$ and n_{eff} , are obtained by solving the equation below:

$$\Delta_t^2 + \left(\frac{2\pi}{\lambda}\right)^2 (n^2 - n_{\text{eff}}^2) E = 0 \quad (2)$$

Where Δ_t is transverse Laplacian operator in the (x,y) direction, while n_{eff} is the effective refractive index of fundamental optical mode,⁹ directly related to Brillouin frequency shift via the Bragg condition.¹⁰ The acoustic wave, which consists of the stress and strain components, are governed by Hooke's Law¹² whereby solving the equation below would yield its displacement.

$$T_{ij} = c_{ijkl} S_{kl}; \quad i, j, kl = x, y, z \quad (3)$$

where T denotes the stress field and S represents the force field which is equivalent to partial differentiation of displacement. c_{ijkl} is the tensor relation of elastic stiffness where i, j, kl are equivalent to propagation in x, y and z direction respectively.²² For an isotropic medium with uniform wave propagation, the elastic stiffness constant is given by the longitudinal and shear velocity that is dependent on the material properties of the optical fiber core and cladding.¹²

For the purpose of calculating the Brillouin gain, the overlap factor from the fully vectorial approach was used. The overlap between optical wave and acoustic wave is given in equation (4) below.²¹

$$\Gamma_{ij} = \frac{\int [|H_i^2(x,y)| |U_j(x,y)|]^2 dA}{\int |H_i(x,y)|^4 dA \int |U_j(x,y)|^2 dA} \quad (4)$$

where $H_i(x, y)$ is the fundamental mode in optical wave and $U_j(x, y)$ is the displacement vector of acoustic wave. Optic-acoustic wave overlap factor is influenced by the acoustic wave's strain field and refractive index of the optical fiber.¹¹ Both the optical and acoustic wave vectors have to be normalized to calculate the overlap factor.

The Brillouin gain coefficient is represented by the equation below:²³

$$g_B(\nu) = g_p = \frac{4\pi^3 n_{eff}^8 p_{12}^2}{c \lambda_p^3 \rho_0 v_B \Delta \nu_B} \quad (5)$$

Where ρ_0 is fiber core density, p_{12} is elasto-optic coefficient which contributes to the periodic light scattering and is FWHM of acoustic wave in SBS.²³

COMSOL parameters

Method in COMSOL

Based on the parameters in Table 1, SBS characterization using the fully vectorial approach was performed on various core diameters of the tapered region of the silica microfiber and was verified against earlier results by H. J. Lee.²³ The n_{eff} were calculated for all core diameters. Refractive index for the core and clad used were 1.4502 and 1.445 respectively considering the measured values in a typical single mode fiber.²¹ Following that, three cases of acoustic wave, shear, longitudinal and hybrid behavior were analyzed.

Optical mode solver

To obtain the n_{eff} results for the two case studies covered in this research, the optical mode equation was solved using the COMSOL RF module. In the RF module the electromagnetic waves, frequency domain physics engine was used. The geometric structures of the fibers were generated using the two dimensional space dimension. From there, the parameters as denoted in Table 1 were entered into the solver. The density, refractive index of both the core and clad values are declared under the materials section. Thereafter, the mode analysis frequency is set to the desired wavelength of 1550 nm and the perfect electrical conductor boundary condition was used. As with all FEM solvers meshing is required. For this case, the triangular mesh and the “finer” element size was used. The effective mode index or n_{eff} for the fundamental mode can thereafter be obtained after computing the solver.

Acoustic mode solver

As for the acoustic model, the acoustic waves of shear and longitudinal were evaluated independently to record the findings. Thereafter, the hybrid acoustic wave across the fiber in which both shear and longitudinal acoustic waves co-exist were examined. The hybrid mode model was the model used to determine the Brillouin Shift Frequency ν_B as both these waves propagate together in real life conditions. Table 2 shows the velocity assigned for core clad region in each respective case. In the case of pure shear acoustic, longitudinal velocity for the core region were made equivalent to 5736 m/s, this is to prevent interruption of longitudinal acoustic wave. Similarly, for pure longitudinal acoustic, the shear acoustic of the core was made to 3625 m/s. For the hybrid acoustic wave, the velocities of both the longitudinal and shear waves of the clad are defined to be slightly higher than the core.²¹ This is to prevent interruption of acoustic wave between the two regions. The core-clad ratio was taken to be 1:3 so that the clad region is long enough to prevent wave reflection from the outer side of clad back to the inner core. Equation 3 being a partial differential equation is solved using the Mathematics physics engine. The weak form PDE interface was used to solve equation 3. Like the optical model, the geometric structures were setup and defined in the model and the values for the acoustic wave for both shear and longitudinal velocities as tabulated in Table 2 were used. The Drichelet boundary condition was used for acoustic model simulation and the mesh setting for the acoustic model is similar with the optical model whereby the triangular

Table 1. Tapered fiber parameters.

Case study	Core (diameter)	Cladding (diameter)	Refractive Index (core/clad)	Density of material ρ (kg/m ³)	Wavelength
1	2 μ m	6 μ m	1.4502/1.445	2202	1550 nm
2	4 μ m	12 μ m			

Table 2. Acoustic velocity parameters for acoustic model simulation.²¹

Case	Region	V_l (m/s)	V_s (m/s)
Shear acoustic	Core	5933	3625
Shear acoustic	Clad	5933	3764
Longitudinal acoustic	Core	5736	3764
Longitudinal acoustic	Clad	5933	3764
Hybrid acoustic	Core	5933	3625
Hybrid acoustic	Clad	5933	3764

mesh was used with the “finer” element size used. Computing the solver would return multiple results of eigenvalues. The eigenvalue returning the fundamental mode plots would be the one selected as the Brillouin Shift Frequency ν_B result.

Results and discussion

The plots in [Figure 1](#) show the Ex, Ey and the Ez components for the optical modes. Based on the numerical model, the n_{eff} was found to be 1.431599.

The plots in [Figure 2](#) show the Ex, Ey and the Ez components for the optical modes respectively. Based on the numerical model, the n_{eff} was found to be 1.441802

[Figure 3](#) shows the pure shear acoustic mode along the silica microfiber where it dominates along x direction. For shear acoustic mode propagation, frequency shift is at 6.61 GHz with acoustic velocity of 3578 m/s.

[Figure 4](#) shows the pure shear acoustic mode along the silica microfiber where it dominates along x direction. For shear acoustic mode propagation, frequency shift is at 6.637 GHz with acoustic velocity of 3567 m/s.

Figure 1. Case study 1: optical results. **Figure 2. Case study 2: optical results.**

Figure 3. Case study 1: acoustic results for shear modes.

Figure 4. Case study 2: acoustic results for shear modes.

Figure 5. Case study 1: acoustic results for longitudinal modes.

Figure 5 shows the pure longitudinal acoustic mode along the silica microfiber where it dominates along z direction. For longitudinal acoustic mode propagation, frequency shift is at 6.634 GHz with acoustic velocity of 3591 m/s.

Figure 6 shows the pure longitudinal acoustic mode along the silica microfiber where it dominates along z direction. For longitudinal acoustic mode propagation, frequency shift is at 6.639 GHz with acoustic velocity of 3568 m/s.

Figure 7 shows the hybrid acoustic mode along the silica microfiber where it dominates along z direction. For hybrid acoustic mode propagation, frequency shift is at 6.611 GHz with acoustic velocity of 3578 m/s.

Figure 8 shows the hybrid acoustic mode along the silica microfiber where it dominates along z direction. For hybrid acoustic mode propagation, frequency shift is at 6.638 GHz with acoustic velocity of 3568 m/s.

From the two case studies simulated using the COMSOL numerical model, we find that the values of the effective refractive index generated by the optical mode model increases as the core and clad diameter increases. The results are recorded in [Table 3](#) below.

Figure 6. Case study 2: acoustic results for longitudinal modes.

Figure 7. Case study 1: acoustic results for hybrid modes.

Figure 8. Case study 2: acoustic results for hybrid modes.

Table 3. Effective refractive index results.

Case study	Core diameter	Clad diameter	Effective refractive index
1	2 μm	6 μm	1.431599
2	4 μm	12 μm	1.441802

Figure 9 demonstrates the relationship between n_{eff} and silica microfiber diameter. n_{eff} in this case here can be seen increasing as the core diameter of optical fiber increases. The n_{eff} value increases ranging from 1.390115 to 1.446122 for 1 μm to 6 μm core diameter of the optical fiber. The values are generated based on the optical model developed in COMSOL. The effective mode index n_{eff} is based on the fundamental mode for these fibers.

From the results obtained and shown in Table 4 based on the acoustic model simulations, the smaller core and clad radius of an optical fiber will produce a lower Brillouin shift frequency compared to an optical fiber with a larger core and clad radii. As for the acoustic velocities observed in the optical fibers, a smaller core and clad radii produces a higher acoustic

Figure 9. Relationship between n_{eff} and silica microfiber diameter.

Table 4. Brillouin shift frequency and acoustic velocity for shear, longitudinal and hybrid modes results.

Case study	1	2
Core diameter	2 μm	4 μm
Cladding diameter	6 μm	12 μm
Brillouin frequency shift for shear modes	6.610 GHz	6.637 GHz
Acoustic velocity for shear modes	3578 m/s	3567 m/s
Brillouin frequency shift for longitudinal modes	6.634 GHz	6.639 GHz
Acoustic velocity for longitudinal modes	3591 m/s	3568 m/s
Brillouin frequency shift for hybrid modes	6.611 GHz	6.638 GHz
Acoustic velocity for hybrid modes	3578 m/s	3568 m/s

Table 5. Overlap ratio.

Core diameter	Clad diameter	Overlap ratio
2 μm	6 μm	0.126
4 μm	12 μm	0.073

Table 6. Brillouin gain.

Core diameter	Clad diameter	Brillouin gain
2 μm	6 μm	1.780×10^{-11} m/W
4 μm	12 μm	3.149×10^{-12} m/W

velocity. The Brillouin frequency shift is due to the optical-acoustic interaction. The overlap integral as stated in [equation 4](#) demonstrates the overlap ratio between the acoustic and optical mode in the optical fiber. Shown below are the overlap ratios with respect to their core diameter. The overlap ratios are obtained by solving the overlap integral equation and are tabulated in [Table 5](#).

From the results in [Table 5](#), it can be seen that the overlap ratio decreases as the core diameter increases.

The Brillouin gain coefficient values can be calculated by substituting the values obtained from the numerical model into the equation as denoted by Equation 5. Table 6 shows the Brillouin gain coefficient for the 2 optical fibers that were modeled.

Conclusion

The main aim of this research is to investigate the Brillouin shift in a tapered silica fiber of different core and clad radii by stimulated Brillouin scattering. To do that, numerical model simulations were developed to study the behavior of the optical wave and acoustic wave propagation in the tapered fiber region. The study on the acoustic wave, which was further divided into three other waves, namely the shear, longitudinal and hybrid mode were evaluated. The hybrid mode would produce the Brillouin shift ν_B which this research is interested in. As the SBS phenomenon benefits from the nonlinearities of a fiber, the present research documents the difference of Brillouin shift frequency between two different core and clad diameters of the tapered fiber region. The Brillouin Frequency Shift ν_B occurs at lower frequencies for a tapered fiber with smaller core and cladding dimensions. Nonlinear effects were also observed to be higher in a smaller diameter fiber based on the overlap factor and Brillouin gain reported. For future work, this COMSOL model can also be used for the following areas of research which includes simulating “Surface Brillouin Shift” and also to provide in-sights to the Brillouin shift frequency ν_B of various structures of waveguides, e.g. circular and triangular, and also to examine specialty fibers, e.g. Thulium and Chalcogenide, and their effects on the Brillouin shift frequency.

Data availability

Underlying data

DRYAD: Dataset of Numerical Model For Enhancing Stimulated Brillouin Scattering In Optical Fibers, <https://doi.org/10.5061/dryad.kd51c5b4w>.²⁴

Data are available under the terms of the Creative Commons Zero “No rights reserved” data waiver (CC0 1.0 Public domain dedication).

Software availability

The COMSOL software is proprietary and requires a subscription for use. The work presented in this article could instead be replicated using the open software tool FreeFEM (<https://freefem.org/>).

References

1. L B: **Diffusion de la lumière et des rayons x par un corps transparent homogène. influence de l'agitation thermique**, *Annual Physic*. 1922; **17**: 88–122.
[Publisher Full Text](#)
2. Vyslouch V: **Nonlinear fiber optics**. 1990; Vol. **160**.
3. Nikles M, Thévenaz L, Robert PA: **Simple distributed fiber sensor based on brillouin gain spectrum analysis**. *Optics Letters*. 1996; **21**(10): 758–760.
[Publisher Full Text](#)
4. Cherif R, Salem AB, Saini TS, et al.: **Design of small core tellurite photonic crystal fiber for slow-light-based application using stimulated brillouin scattering**. *Optical Engineering*. 2015; **54**(7): 75101–75101.
[Publisher Full Text](#)
5. Song KY, Abedin KS, Hotate K, et al.: **Highly efficient brillouin slow and fast light using as2se3 chalcogenide fiber**. *Opt Express*. 2006; **14**(13): 5860–5865.
[PubMed Abstract](#) | [Publisher Full Text](#)
6. Woodward RI, Kelleher EJR, Popov SV, et al.: 2014.
7. Tchahame J, Beugnot J, Maillotte H, et al.: **Multimode brillouin scattering in a long tapered photonic crystal fiber**, *The European Conference on Lasers and Electro-Optics*. 2015; **25**.
8. Beugnot J, Lebrun S, Pauliat G, et al.: 2014.
9. Hu K, Kabakova IV, Büttner T, et al.: **Low-threshold brillouin laser at 2 mm based on suspended-core chalcogenide fiber**. *Opt Lett*. 2014; **39**(16): 4651–4654.
[PubMed Abstract](#) | [Publisher Full Text](#)
10. Kim M, Besner S, Ramier A, et al.: **Shear Brillouin light scattering microscope**. 2016; **24**(1): 319–328.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
11. Rahman BMA, Agrawal A: **Finite Element Modeling Methods for Photonics**. *Artech House*. 2013.
12. Rahman BMA, Davies JB: **Finite-element solution of integrated optical waveguides**. *J Lightwave Technol*. 1984; **2**(5): 682–688.
[Publisher Full Text](#)
13. Poulton CG, Pant R, Eggleton BJ: **Acoustic confinement and stimulated brillouin scattering in integrated optical waveguides**. *JOSA B*. 2013; **30**(10): 2657–2664.
[Publisher Full Text](#)
14. Hughes TJ: **The finite element method: linear static and dynamic finite element analysis**. Courier Corporation; 2012.
15. Rahman BA, Davies JB: **Penalty function improvement of waveguide solution by finite elements** *Microwave Theory and Techniques. IEEE Transactions*. 1984; vol. **32**, no. 8, pp. 922–928.
[Publisher Full Text](#)
16. Ham S, Bathe K-J: **A finite element method enriched for wave propagation problems**. *Computers & Structures*. 2012; **94**: 1–12.
[Publisher Full Text](#)
17. Sriratanavaree S, Rahman B, Leung D, et al.: **Rigorous characterization of acoustic-optical interactions in silicon slot waveguides by full-vectorial finite element method**. *Opt Express*. 2014; **22**(8): 9528–9537.
[PubMed Abstract](#) | [Publisher Full Text](#)
18. Monfared V, Mondali M: **Semi-analytically presenting the creep strain rate and quasi shear-lag model as well as finite element method prediction of creep debonding in short fiber composites**. *Materials & Design*. 2014; **54**: 368–374.
[Publisher Full Text](#)
19. Liu X, Liu N, Su X, et al.: **Numerical analysis of fibers tensions in the siro-spinning triangle using finite element method**. *Fibers Polymers*. 2015; **16**(1): 209–215.
[Publisher Full Text](#)
20. Lee HJ, Abdullah F, Emami SD, et al.: **Fiber modeling and simulation of effective refractive index for**

- tapered fiber with finite element method. 2016 IEEE 6th International Conference on Photonics (ICP), Kuching, Malaysia. 2016; pp. 1-3.
[Publisher Full Text](#)
21. Sriiratanavaree S: **The characterisation of acoustic waves in optical waveguides.** 2014.
 22. Gan WS: **New Acoustics Based on Metamaterials.** 2017.
 23. Lee HJ: **Modelling of Stimulated Brillouin Scattering in Graphene-clad tapered fiber using Finite Element Method.**
 24. Abdul-Rashid: **Dataset of Numerical Model For Enhancing Stimulated Brillouin Scattering In Optical Fibers.** *DRYAD [dataset]*. 2021.
[Publisher Full Text](#)

Open Peer Review

Current Peer Review Status:

Version 1

Reviewer Report 11 November 2021

<https://doi.org/10.5256/f1000research.54134.r88748>

© 2021 A Bakar A. This is an open access peer review report distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Ahmad Ashrif A Bakar

¹ Department of Electrical, Electronic and Systems Engineering, Universiti Kebangsaan Malaysia, Bangi, Malaysia

² Universiti Kebangsaan , Kuala Lumpur, Malaysia

This paper demonstrates the enhancement of stimulated Brillouin scattering in optical microfibers using a numerical model vectorial approach. The Brillouin shift by stimulated Brillouin scattering in a tapered silica fiber of different core and clad radii were investigated. I would suggest the authors have some amendments to improve the quality of the article. The comments are as follows.

1. Would you please put more insight into the results and discussion? The explanation of the results is too brief.
2. I'd recommend the authors to put more discussion in Figure 9 as well. It'd be interesting to see why the graphs are linear in the first stage and gradually saturated once the core diameter reaches 2µm and above.

Is the rationale for developing the new method (or application) clearly explained?

Yes

Is the description of the method technically sound?

Yes

Are sufficient details provided to allow replication of the method development and its use by others?

Yes

If any results are presented, are all the source data underlying the results available to ensure full reproducibility?

Yes

Are the conclusions about the method and its performance adequately supported by the findings presented in the article?

Yes

Competing Interests: No competing interests were disclosed.

Reviewer Expertise: Photonics sensing devices, surface plasmon resonance, optical feedback interferometry

I confirm that I have read this submission and believe that I have an appropriate level of expertise to confirm that it is of an acceptable scientific standard, however I have significant reservations, as outlined above.

Author Response 30 Jan 2022

Hairul Azhar Abdul-Rashid, Multimedia University, Cyberjaya, Malaysia

Thank you for the comments made to the manuscript and questions raised. We have added to the discussion as follows:

Figure 9 demonstrates the relationship between n_{eff} and silica microfiber diameter. n_{eff} in this case here can be seen increasing as the core diameter of optical fiber increases. The n_{eff} value increases ranging from 1.390115 to 1.446122 for 1 μm to 6 μm core diameter of the optical fiber. The values are generated based on the optical model developed in COMSOL. Based on the findings observed, the effective refractive index n_{eff} starts to no longer fall within the core and clad refractive index window for uniform microfibers that have core diameters 6 μm and below. This is due to the fact that modes propagating in the microfiber are no longer guided by the core and clad interface but by the air-cladding interface. It becomes more and more pronounced as the core diameter decreases.

From the results obtained and shown in Table 4 based on the acoustic model simulations, the smaller core and clad radius of an optical fiber will produce a lower Brillouin shift frequency compared to an optical fiber with a larger core and clad radii. As for the acoustic velocities observed in the optical fibers, a smaller core and clad radii produces a higher acoustic velocity. The Brillouin Frequency shift tabulated in table 4 is obtained from the fundamental eigenvalue based on the numerical model results obtained from the COMSOL model. The Brillouin frequency shift is due to the optical-acoustic interaction. The overlap integral as stated in equation 4 demonstrates the overlap ratio between the acoustic and optical mode in the optical fiber. Shown below are the overlap ratios with respect to their core diameter. The overlap ratios are obtained by solving the overlap integral equation and are tabulated in Table 5

From the results in Table 5, the overlap ratio is influenced by the core and cladding diameter and subsequently affect the Brillouin gain and frequency shift. This is clearly due to the optical mode and acoustic mode profile influenced by the core and cladding diameter. Based on our simulations, a typical silica uniform microfiber with parameters as mentioned above would observed a Brillouin Frequency shift around the 6GHz window. The

Brillouin frequency shift for the individual modes namely shear, longitudinal and hybrid were observed to occur at the lower end of the 6GHz spectrum for microfibers that have a smaller core and clad dimensions. As the core and clad dimensions' increase, we observe the Brillouin Frequency shift to occur at a higher frequency in the 6GHz spectrum. The numerical model therefore helps provide insights into fiber sensor development depending on the sensing frequency of interest. A higher acoustic velocity observed in smaller core and clad fibers also increase the overlap factor of the fundamental modes respectively. In fiber sensors, exposure to external perturbations like temperature will in effect change the acoustic velocity and the Brillouin shift frequency.

The Brillouin gain coefficient values can be calculated by substituting the values obtained from the numerical model into the equation as denoted by Equation 5.

Table 6 shows the Brillouin gain coefficient for the 2 optical fibers that were modeled. Between the 2 fibers modelled using the numerical model, it was observed that the optical fiber core and clad dimensions of 2 and 6 μm respectively has a higher Brillouin gain coefficient. The higher Brillouin gain coefficient is attributed to the higher overlap ratio, as shown in Table 5. One can relate this understanding to optimize the design of Brillouin amplifiers and sensors with the appropriate Brillouin gain coefficient. Thus, the numerical model here provides insights to the sensor design based on the requirements needed (25).

Competing Interests: No competing interests were disclosed.

Reviewer Report 23 August 2021

<https://doi.org/10.5256/f1000research.54134.r88747>

© 2021 Peng G. This is an open access peer review report distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Gand Ding Peng

School of Electrical Engineering and Telecommunications, University of New South Wales, Sydney, NSW, Australia

Enhancing stimulated Brillouin scattering in optical fibres is of great importance in many applications such as optical fibre sensing and optical signal amplification. In this paper, the authors presented how to numerically model SBS in silica optical fibre in terms of Brillouin frequency shift and Brillouin gain coefficient - which are the two most fundamental yet important parameters of concern.

I read through with great interest and was helped by the fact that the paper has presented a comprehensive overview of reported work from related reference papers.

The paper reported interesting and useful results on how fibre parameters and effective refractive index affect Brillouin frequency shift and Brillouin gain coefficient. There are issues that may need

to be addressed and clarified:

For the two cases studied, the resulted effective indexes are found to be 1.431599 and 1.441802, respectively. I note that the core and cladding refractive Indexes used in the simulation are 1.4502 and 1.445, respectively. Normally we would expect that the effective index of optical mode to be within core and cladding indexes, i.e. between 1.4502 and 1.445. Why both the effective indexes are lower than 1.445 here?

In describing the method to obtain Brillouin frequency shift and gain coefficient, it is not clear how the optical - acoustic wave overlap factor (equation 4) is related to the Brillouin gain coefficient (equation 5). A simple explanation would be helpful. In addition, It would be helpful to explain how the Brillouin frequency shift is determined.

It is not very clear how the values of sheer and longitudinal velocities are assigned for core and clad for different cases. For example, it is stated that 'in the case of pure shear acoustic, longitudinal velocity for the core region were made equivalent to 5736 m/s, this is to prevent interruption of longitudinal acoustic wave'. Please explain what 'interruption' means here. (Please note: the actual value for longitudinal acoustic wave velocity in the shear acoustic case in Table 2 is 5933, not 5736 as stated.)

In the abstract, it is stated that 'This paper describes the method related to the numerical model and discusses the analysis between the interactions of horizontal, shear and hybrid acoustic modes; and optical modes in optical fiber'. But the rest of the paper 'horizontal' is replaced with 'longitudinal'. It would be better to keep consistency. In addition, more analysis/discussion of the interaction of these acoustic modes would be helpful.

In this paper, it frequently referred to the two cases of different core sizes (with the same core/cladding ratio) as tapered fibre. This is not really tapered fibre cases anyway. They are just two straight optical fibre cases. The use of tapered fibre is a bit confusing. For example, in the conclusion, it is stated that 'The Brillouin Frequency Shift ν_B occurs at lower frequencies for a tapered fiber with smaller core and cladding dimensions'. Here 'for a tapered fiber' seems inaccurate since the results are based on numerical simulation of a uniform fibre case.

In the paper, it has used 'Brillouin gain coefficient' and 'Brillouin gain' alternatively. It must be noted that they are two distinctive parameters with different units normally. For example, in the abstract, it is mentioned as 'gain' in the statement 'Based on this numerical model, we report the influence of core radius, clad radius, and effective refractive index on the Brillouin frequency shift and gain'. Similarly, Table 6 should be 'Brillouin gain coefficient' and 'Brillouin gain'. Perhaps 'gain coefficient', instead of 'Brillouin gain', is a slightly better alternative for 'Brillouin gain coefficient' if needed.

Some of the references didn't include the sources. For example, refs 21-23.

Finally, the authors may check spelling and wording for better clarity For example, it is stated in the abstract that 'SBS was previously viewed as a poor method due to the limitation on optical power in high-powered photonic applications'. It seems to me that 'method' is not an appropriate term here.

In summary, although there are aspects that the paper could be improved upon as mentioned above, the paper presented an important work of interest to people in the field and is worthy of indexing and further working on.

Is the rationale for developing the new method (or application) clearly explained?

Yes

Is the description of the method technically sound?

Yes

Are sufficient details provided to allow replication of the method development and its use by others?

Partly

If any results are presented, are all the source data underlying the results available to ensure full reproducibility?

Partly

Are the conclusions about the method and its performance adequately supported by the findings presented in the article?

Yes

Competing Interests: No competing interests were disclosed.

Reviewer Expertise: Photonics and Optical Fibres

I confirm that I have read this submission and believe that I have an appropriate level of expertise to confirm that it is of an acceptable scientific standard.

The benefits of publishing with F1000Research:

- Your article is published within days, with no editorial bias
- You can publish traditional articles, null/negative results, case reports, data notes and more
- The peer review process is transparent and collaborative
- Your article is indexed in PubMed after passing peer review
- Dedicated customer support at every stage

For pre-submission enquiries, contact research@f1000.com

F1000Research