REVIEW

Advancing cardiovascular tissue engineering [version 1; peer review: 3 approved]

George A. Truskey

Department of Biochemical Engineering, Duke University, Durham, NC, USA

V1 First published: 31 May 2016, 5(F1000 Faculty Rev):1045
<https://doi.org/10.12688/f1000research.8237.1>

Latest published: 31 May 2016, 5(F1000 Faculty Rev):1045
<https://doi.org/10.12688/f1000research.8237.1>

Abstract

Cardiovascular tissue engineering offers the promise of biologically based repair of injured and damaged blood vessels, valves, and cardiac tissue. Major advances in cardiovascular tissue engineering over the past few years involve improved methods to promote the establishment and differentiation of induced pluripotent stem cells (iPSCs), scaffolds from decellularized tissue that may produce more highly differentiated tissues and advance clinical translation, improved methods to promote vascularization, and novel *in vitro* microphysiological systems to model normal and diseased tissue function. iPSC technology holds great promise, but robust methods are needed to further promote differentiation. Differentiation can be further enhanced with chemical, electrical, or mechanical stimuli.

Keywords

Tissue engineering, cardiovascular, iPSCs

Open Peer Review

Approval Status

	1	2	3
version 1 31 May 2016			

Faculty Reviews are review articles written by the prestigious Members of **Faculty Opinions**. The articles are commissioned and peer reviewed before publication to ensure that the final, published version is comprehensive and accessible. The reviewers who approved the final version are listed with their names and affiliations.

1. **David Schaffer**, University of California, Berkeley, Berkeley, USA
2. **Gordana Vunjak-Novakovic**, Columbia University, New York, USA
3. **Irving H Zucker**, University of Nebraska Medical Center, Omaha, USA

Any comments on the article can be found at the end of the article.

Corresponding author: George A. Truskey (george.truskey@duke.edu)

Competing interests: The author declares that he has no competing interests.

Grant information: This work was supported, in part, by NIH grant UH3TR000505.

The funders had no role in study design, data collection and analysis, decision to publish, or preparation of the manuscript.

Copyright: © 2016 Truskey GA. This is an open access article distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

How to cite this article: Truskey GA. **Advancing cardiovascular tissue engineering [version 1; peer review: 3 approved]**

F1000Research 2016, 5(F1000 Faculty Rev):1045 <https://doi.org/10.12688/f1000research.8237.1>

First published: 31 May 2016, 5(F1000 Faculty Rev):1045 <https://doi.org/10.12688/f1000research.8237.1>

Introduction

Tissue engineering involves the development of functional replacements for damaged tissues or organs (<http://www.nibib.nih.gov/science-education/science-topics/tissue-engineering-and-regenerative-medicine>). A common approach to produce engineered tissues is to add cells to a natural or synthetic extracellular matrix, which provides mechanical support and biochemical cues. Scaffold-free tissues are prepared by growing cells on thermally responsive polymers to facilitate the cell monolayers that form and then adding layers together or rolling the sheets. By addition of small molecules that activate specific differentiation pathways, three-dimensional organoids can be derived from human pluripotent stem cells¹. The engineered tissue may be prepared wholly or partially before implantation to activate and localize the body's regenerative capacity to populate the implanted scaffold. Tissue engineering is a subset of the broader field of regenerative medicine, which seeks to repair or replace damaged organs. This could occur by direct injection of cells or modifying cellular processes to initiate repair and regrowth. In spite of significant research advances and insightful application of developmental cell biology, cell mechanics, and biomaterials, few products have emerged from these efforts to date, pointing to the challenges to develop truly functional tissues.

Key design goals to produce functional tissues *in vitro* are to reproduce the tissue structure and cell density *in vivo*, identify suitable sources of cells, promote growth and differentiation of cells, design a construct that reproduces the extracellular matrix with the appropriate molecular cues and suitable mechanical properties, and create a vasculature within the construct to enable oxygenation and integration with host vasculature after implantation.

Several strategies that have emerged to address these challenges include the use of induced pluripotent stem cells (iPSCs) or embryonic stem cells (ESCs) that can differentiate into the cells of interest, the reprogramming of primary cells to the cell type of interest, various ways to engineer the structural support for the cells to mimic the extracellular matrix, and efforts to promote vascular network formation (Figure 1). Over the past few years, a new use of tissue engineering has emerged in which microscale human tissue-engineered systems or microphysiological systems are used to model normal and disease states *in vitro* and assess drug responses.

Recent advances in tissue engineering over the past three years were recently summarized in two reviews^{2,3}. Given the breadth of tissue engineering research (13,661 publications since 1 January 2014 reported on Google Scholar), we focus this summary of recent work on cardiovascular tissue engineering as a way to demonstrate how new research results have addressed the key design challenges. Cardiovascular tissue engineering is a vibrant area of research, and applications in the cardiovascular system include cardiac patches, engineered blood vessels and heart valves, and vascular networks.

Scaffolds

Scaffold materials should match the mechanical properties of the tissue and undergo degradation or be integrated into the tissue, allowing the natural extracellular matrix to replace the original structural support. Materials used in cardiovascular tissue engineering include degradable polymers, such as polyglycolic acid⁴ and polylactic acid, as well as biological hydrogels, such as collagen⁵, fibrin⁶, and modified hyaluronic acid⁷. These scaffold materials can be modified by the addition of cell adhesion domains or sites

Figure 1. Schematic of processes to produce cell-based engineered cardiac or vascular tissue. Primary cells or induced pluripotent stem (iPS) cells undergo a period of proliferation prior to seeding into a three-dimensional scaffold or are grown as sheets on a polymer whose conformation changes in response to temperature or other stimuli, enabling detachment on the sheet. During the proliferation phase, microRNAs or transcription factors may be added to the cells to promote subsequent differentiation. To promote further differentiation, small molecules are added and/or cells are exposed to electrical or mechanical stimuli. Endothelial cells added to the tissue during formation promote vascular network formation. After the cells have reached a certain level of maturity, the engineered tissue is implanted and the host blood supply connects with the vascular network promoted by endothelial cells. Alternatively, cells may be encapsulated in a biodegradable polymer and implanted.

susceptible to cleavage by matrix metalloproteinases to facilitate cell attachment and migration. Alternatively, sheets of cells can be prepared and then fabricated into different configurations such as tubes or patches. Such structures have high mechanical strength and function well *in vivo*⁸. This approach has the advantage of not needing any synthetic polymers.

A scaffold-free cardiac patch consisting of three layers of rat cardiomyocytes was successfully engrafted onto heart tissue by overlaying the patch over a vascular supply, enhancing the ability of endothelial cells (ECs) in the patch to form a functional tubular vascular network connected to the host blood supply⁹. Recently, the development of a porous patch with an electroactive polypyrrole incorporating electronics for sensing and stimulating electrophysiological activity and release of various biological molecules offers a new level of control of cardiac patches while permitting incorporation of cells attached to a bioactive scaffold¹⁰.

While tissue-engineered blood vessels (TEBVs) constructed from natural matrix components such as collagen^{11,12} and fibrin^{13,14} have traditionally exhibited poor mechanical strength, plastic compression of collagen gels embedded with smooth muscle cells (SMCs) increases the collagen fiber density and yields rapidly producible tubular structures with high mechanical strength¹⁵. By plastic compression of collagen, TEBVs with burst pressures exceeding 1600 mmHg can be prepared in a few hours⁵. After one week of perfusion at physiological shear stresses, the medial cells exhibited differentiation and contracted in response to phenylephrine. While these TEBVs have not been studied *in vivo*, this rapid method of fabrication could significantly reduce the time to produce functional TEBVs.

Decellularized tissue contains many of the cues needed for cells to differentiate and responds dynamically after implantation, owing to cellular infiltration and imposed biomechanical loads. For example, after implantation of decellularized valves in sheep, collagen reorganized, responding to biomechanical stresses¹⁶. Increased waviness of collagen corresponded to areas of greater elastin synthesis¹⁶. Decellularization does cause loss and damage to some extracellular matrix proteins. To overcome this limitation, the addition of hyaluronic acid supplement enhanced adhesion in decellularized heart tissue¹⁷. While decellularized tissue as thick as 1–1.5 cm can be produced, mesenchymal stem cells (MSCs) added to the decellularized constructs reached a cell density of 30 million cells/cm³ but occupied only the outer 100 µm of the decellularized heart, suggesting that their growth was limited by oxygen levels. When the constructs were perfused, cells migrated as far as 400 µm into the decellularized tissue. The decellularized heart could support cardiomyocyte function as demonstrated by ESCs that exhibited beating three days after seeding¹⁷.

Decellularized grafts can be modified to enhance their key functions. Immobilization of heparin to decellularized blood vessels using click chemistry reduced platelet adhesion and promoted EC attachment without altering the graft mechanical behavior¹⁸. Selective attachment of biological molecules is preferable to passive adsorption in attempting to compensate for damage to the extracellular

matrix during removal of cells. Rather than harvest and remove cells from blood vessels, the extracellular matrix synthesized by cultured SMCs can be used to create decellularized vessels in a tubular polyglycolic acid scaffold¹⁹, thus providing a more controlled source of readily available extracellular matrix. A similar approach was used to create decellularized heart valves²⁰, which were repopulated with cells eight weeks after implantation and performed better than decellularized valves.

For valve leaflets, the need to have regional variations in cell types and material properties was achieved using decellularized valves or using injection molding²¹ or three-dimensional bioprinting⁷ to fabricate specific three-dimensional shapes. Since decellularized tissue can be formed into hydrogels²² or electrospun, the use of different fabrication methods creates the possibility of precisely designing the tissue to be replaced.

A novel approach to generate the entire TEBV *in vivo* involves taking advantage of the foreign body response and implanting a mandrel subcutaneously around which a tubular tissue grows over a four-week period²³. Initially, the graft consisted of extracellular matrix and fibroblasts with a layer of M1 macrophages. After forming an end-to-end carotid anastomosis in the pig, the macrophages disappeared. After four weeks of grafting, the gene expression profile became similar to that of the carotid artery and fibroblasts adopted a contractile phenotype. The mechanical strength was very good but was less than values for actual vessels. This is a promising approach to develop engineered blood vessels, and other applications involve contracting SMCs (e.g. the bladder), which can be derived from fibroblasts involved in the foreign body response. Extending to other organ systems with specialized cells may prove difficult.

Stem cells for tissue engineering

iPSCs offer the potential to develop engineered tissues of individual human cardiovascular disease states and avoid ethical issues associated with ESCs. iPSCs can be induced to differentiate into a large number of cell types including cardiomyocytes, SMCs^{24,25}, and ECs²⁴. The formation of teratomas²⁶ can be reduced using non-integrating methods²⁷ and immunogenicity is low²⁸. An exciting new development has been the creation of mouse iPSCs using small molecules that activate specific transcription factors²⁹, although this approach has not yet been demonstrated with human iPSCs. A challenge with the use of iPSCs in tissue engineering is that differentiation is often limited and the resulting structures do not display a mature phenotype^{30,31}.

Vascular cells can be obtained from iPSCs or ESCs by first activating the Wnt signaling pathway. Early activation of Wnt and β-catenin by inhibition of glycogen synthase kinase 3 (GSK3) before differentiation on surfaces with serum produces cardiomyocytes³². Following Wnt pathway activation with GSK3 inhibitors, ECs can be obtained by addition of vascular endothelial growth factor (VEGF) and forskolin, while SMCs can be obtained using platelet-derived growth factor-BB (PDGF-BB) and ActivinA²⁵. Interestingly, a recent report indicated that by culturing murine iPSCs on gelatin-coated polycaprolactone nanofibrous scaffolds,

Wnt/ β -catenin can be transiently activated to induce differentiation towards cardiomyocytes³³. Combining GSK3 inhibitors with specific modification of substrate properties may lead to more robust differentiation.

One week of electrical stimulation at 0.5, 1, or 2 Hz of human ESCs or iPSCs in three-dimensional engineered tissues facilitates differentiation to cardiomyocytes by producing hypertrophy, an increase in connexin-43 gap junctions, and increased expression of hERG, the potassium channel which regulates cardiomyocyte repolarization³⁴. Some connexin-40 is expressed, indicating that rapidly conducting cells can be stimulated; however, it is not yet possible to regulate the relative expression of the various connexins through selection of a specific stimulation protocol. The stimulated cells responded to chronotropic drugs and the cells maintained synchrony to the rate of applied stimulation for two weeks after the stimulation ended.

Cardiomyocytes generated by selecting for Nkx2-5-positive cells among mouse iPSCs exhibit a number of markers found in mature cardiomyocytes, and the resting membrane potential approaches physiological levels³⁵. Three-dimensional engineered tissues produced aligned cardiomyocytes that exhibited adherens and gap junctions, although the electrophysiological responses were similar to those exhibited by fetal cardiomyocytes³⁵.

Human ESCs in three-dimensional patches showed extensive maturation and exhibited β -adrenergic responses in the physiological range⁶. Engineered cardiac tissue derived from human ESCs integrated into damaged mouse myocardium and formed a vasculature connected to the host blood supply after 28 days but did not improve heart function owing to extensive cell loss³⁶. Alternatively, partial reprogramming of cardiac fibroblasts can be done using viral transfection of transcription factors, a cocktail of small molecules or microRNAs that activate key transcription factors (e.g. Mef2c, myocardin, and serum response factor). These approaches have yielded some success in producing spontaneously contracting cells, although the frequency of these cells among the population is low³⁷.

Culturing human cardiac myocytes derived from iPSCs on polydimethylsiloxane (PDMS) membranes coated with Matrigel for one week led to significant maturation of the cardiac cells in which the action potential upstroke velocity increased and conduction velocities were twice the value found when the cells were grown on Matrigel-coated glass coverslips³⁸, although this value was still about 57% of the *in vivo* value. This increased maturation was due to a substantial increase in increased inward rectifier potassium and sodium inward current densities, elevated connexin-43 protein expression, hypertrophy of the cardiomyocytes, and increased cardiac troponin β , integrin and focal adhesion kinase. The elastic modulus of the PDMS is approximately 4 MPa, much lower than the modulus of glass (~50 GPa), and the PDMS modulus is much greater than the modulus of cardiac tissue (0.1 MPa)³⁹, suggesting that substrates with lower elastic modulus might enhance differentiation further. Modulating the substrate stiffness together with mechanical loading and electrical stimulation, which promote physiological force-frequency and force-length relations⁴⁰, could

produce cardiomyocytes with *in vivo* electrical and mechanical properties.

The use of small molecules to differentiate iPSCs has been used to create highly differentiated ECs that model the high transport resistance of brain ECs⁴¹. A number of cardiac disease models have been generated using iPSC technology and could replicate the response to cardiotoxic drugs using cells from various individuals⁴². The technology can also be used to assess the adaptive response to dilated cardiomyopathy. For example, cardiomyocytes derived from iPSCs of healthy individuals using small molecules exhibited many of the molecules involved in β -adrenergic signaling and isoproterenol treatment induced inotropic and chronotropic regulation of contractile function⁴³. However, cardiomyocytes derived from iPSCs of individuals with dilated cardiomyopathy exhibited abnormal sarcomere structure and deficits in contractile force, calcium handling, and beat frequency after treatment with isoproterenol that was traced to overexpression of phosphodiesterases 2 and 3a⁴³.

TEBVs fabricated with SMCs derived from murine⁴⁴ and human⁴⁵ iPSCs maintained their differentiated phenotype after subcutaneous implantation for two weeks. Contractile TEBVs with SMCs differentiated from iPSCs developed from human foreskin fibroblasts and MSCs demonstrated intermediate and late SMC proteins⁴⁶. While TEBVs derived from karyotypically normal human iPSC clones function well and express mid-differentiation markers SM-22 α and calponin and secreted extracellular matrix, those derived from karyotypically abnormal clones exhibit senescence, shortened telomeres, and calcification⁴.

Human blood-derived ECs can be reprogrammed to SMCs by activating myocardin using a lentivirus system⁴⁷. Functional TEBVs were produced with these cells that exhibited flow-mediated vasodilation and vasoconstriction in the presence of 1 μ M phenylephrine⁴⁷. While the vasoactivity was somewhat less than that of primary cells⁵, the results do show that TEBVs can be recreated with cells from a single donor.

Vascularization

The density and thickness of engineered tissues is limited by the transport of nutrients to the cells. Oxygen is often the limiting nutrient, since it is consumed at the highest rate and is critical for producing the energy needed for normal cell function. *In vivo*, capillary distances range from 15–50 μ m depending on the cell density and the metabolic demands⁴⁸. *In vitro*, cell densities are lower, but uniform cell densities can be achieved only for thicknesses of about 100 μ m owing to consumption of oxygen in the engineered tissue. Perfusion can lead to somewhat thicker tissues. However, without its own microvascular network that could integrate with the host network after implantation, only thin tissue-engineered constructs can remain viable after implantation.

While addition of VEGF can initiate the formation of new capillaries or branches from existing capillaries *in vitro*, the resulting structures are unstable and last at most a few days. New vessel formation involves several discrete stages. Initially, exogenous VEGF causes the release of matrix metalloproteinases, which

degrade the extracellular matrix, enabling migration of the newly forming vessel buds. The newly forming vessel secretes growth factors to recruit mural cells, such as fibroblasts, pericytes, or SMCs, which interact with the newly formed microvessels, stabilizing them.

Although MSCs can stabilize EC networks *in vitro* and exhibit pericyte-like behavior⁴⁹, the heterogeneity of MSCs from various sources or by different isolation methods leads to variable responses⁵⁰. The cells must be characterized and tested for their ability to stabilize networks when developing a system to create microvascular networks. iPSCs could provide a ready source of pericytes⁵¹, although SMCs or fibroblasts derived from iPSCs may be suitable.

A potentially useful model system to identify conditions that promote vascularization of tissue-engineered systems involves creating microvascular networks in a synthetic extracellular matrix hydrogel. The hydrogel contains matrix metalloproteinase degradation sites and peptide sequences of extracellular matrix proteins to elicit specific cell binding⁵². Photopolymerization of polyethylene glycol gels enables straightforward incorporation of cells, and the networks are robust and sensitive to perfusion in the extracellular space⁵². The direction of flow is very critical for improving mass transfer and enabling microvessels to stabilize⁵³. The extracellular matrix peptide sequences provided influence the extent of network formation, with addition of cell binding sequences from both fibronectin (RGD) and laminin (YIGSR) producing the most robust network formation in the hydrogel⁵⁴. Adding macrophages enhanced new vessel formation in synthetic hydrogels, consistent with their role *in vivo*⁵⁵. Other factors to enhance microvessel network formation in hydrogels involve regulating growth factor delivery⁵⁶ and a hypoxic environment⁵⁷.

Several approaches have been taken to incorporate vascular networks into tissue-engineered constructs for implantation. When ECs were added with MSCs to decellularized heart tissue, vascular networks formed and enabled cell growth further into the construct than could be accomplished with MSCs alone¹⁷. The resulting network may have facilitated more effective fluid and nutrient transport throughout the decellularized tissue.

EC cords show promise as a method to create functional microvascular networks in engineered constructs^{58,59}. The cords are formed by mixing ECs and mural cells in collagen. After shrinkage by 50% in diameter over four hours, the cords are encased in fibrin and integrated into the tissue-engineered construct⁵⁸. After implantation of cords into mice, capillaries formed within seven days and matured by 14 days. Red cells were observed in the lumen and an EC monolayer formed, defining the capillary border⁵⁸. The capillaries involved both donor and host ECs. When the EC and MSC cords were added with hepatic construct, they improved key hepatocyte functions⁵⁸. Cord diameters of 25, 75, and 250 μm all produced functional capillary networks, although smaller cords produced a higher density of vessels and the larger cords led to more dispersed vessels⁵⁹. Mural cells were not necessary to form functioning capillaries after implantation, possibly owing to the involvement of host

mural cells⁵⁹. This approach can be used to control the density and geometry of the microvascular network, two properties that vary based on demand and function of the tissue.

Microphysiological systems

High-throughput screens for function or to test drugs are being developed by integrating tissue engineering, microfluidics, and advanced methods of sensing. The National Center for Advancing Translational Science (NCATS) at NIH and the Defense Advanced Research Programs Association have led an effort to advance individual microphysiological systems and examine interactions among different organ systems. Microphysiological systems have been developed for the heart^{34,60}, blood vessels⁵, microcirculation⁵³, kidney⁶¹, gut⁶², lung⁶³, liver⁶⁴, skeletal muscle⁶⁵, and female reproductive tract⁶⁶. The small size of the systems reduces or eliminates mass transfer limitations, and function can be monitored with sensors or reporter systems. These systems have been developed using a combination of primary human cells and iPSCs. iPSCs provide the ability to create patient-specific cardiovascular disease models owing to their ability to maintain the disease phenotype post-differentiation^{67,68}. Gene editing makes feasible isogenic controls for *in vitro* studies⁶⁹.

Microphysiological systems based on the cardiovascular system reproduce key functions and known drug responses. Human endothelialized TEBVs with inner diameters of 500–800 μm exhibit a dose-dependent contraction in response to phenylephrine and a dose-dependent relaxation following exposure to acetylcholine over five weeks in culture⁵. The TEBVs elicited reversible activation to acute inflammatory stimulation by TNF- α , which was blocked by pre-treating the TEBVs with statins⁵ and consistent with the pleotropic effect that statins exert on ECs⁷⁰.

Several different microphysiological systems have been developed to model cardiac function. In one, cardiomyocytes are grown on poly(N-isopropylacrylamide) (PIPAAm) in a microfluidic chamber⁷¹. Forces exerted by contracting cardiomyocytes are determined from deformation of PIPAAm. As many as 28 PIPAAm cantilevers can be incorporated in one chip, and the fluidics enable easy exchange after drug or agonist exposure. This system was used to study Barth syndrome, an X-linked mutation of an acyltransferase essential for modification of cardiolipin. Individuals with this syndrome die within a year of birth due to heart failure and/or infection. This cardiac microphysiological system showed reduced contractile stresses by cardiomyocytes derived from Barth syndrome iPSCs⁷². Contractile stresses returned to normal for cells treated with a modified RNA that corrected the mutation and was improved after treatment with linoleic acid⁷², suggesting a novel treatment. An alternative approach to quantify contraction involves measuring strains using digital image correlation software to analyze the deformation of the engineered muscle³⁴. To convert to stress, the stress-strain behavior of the muscle is needed.

Another system provided short transport distances and confined cardiomyocytes at high cell density in a microfluidic chamber⁶⁰. The confinement barrier mimics the diffusive resistance of an endothelial monolayer but lacks the biochemical signals that arise

from EC-cardiomyocyte interactions. Aligned and synchronously beating human cardiomyocytes derived from iPSCs were produced over a period of seven days. Cardiac cell motion was analyzed using custom software and was found to accurately represent cardiac cell responses to calcium channel and hERG blockers and β -adrenergic agonists and antagonists. The system can easily integrate the measurement of reporter fluorescence assays and analysis of the media after perfusion⁶⁰.

Summary and future directions

New technologies to promote cell differentiation and vascularize engineered constructs address key challenges in making viable engineered tissues that can be implanted. At the same time, decellularized tissues, either derived from organs and tissues or fabricated in the lab, make available an alternative approach to tissue engineering in which the implanted matrix serves as a substrate to guide cell repopulation and differentiation after implantation. Both approaches have aided our understanding of the complex

interactions between cells and the extracellular matrix in producing a functional tissue.

Competing interests

The author declares that he has no competing interests.

Grant information

This work was supported, in part, by NIH grant UH3TR000505.

The funders had no role in study design, data collection and analysis, decision to publish, or preparation of the manuscript.

Acknowledgements

I appreciate the many helpful conversations with my colleagues Nenad Bursac and William Kraus and students Cristina Fernandez and Leigh Atchison.

References

1. Jones JR, Zhang SC: **Engineering human cells and tissues through pluripotent stem cells.** *Curr Opin Biotechnol.* 2016; **40**: 133–8.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
2. Harrison RH, St-Pierre JP, Stevens MM: **Tissue engineering and regenerative medicine: a year in review.** *Tissue Eng Part B Rev.* 2014; **20**(1): 1–16.
[PubMed Abstract](#) | [Publisher Full Text](#)
3. Wobma H, Vunjak-Novakovic G: **Tissue Engineering and Regenerative Medicine 2015: A Year in Review.** *Tissue Eng Part B Rev.* 2016; **22**(2): 101–13.
[PubMed Abstract](#) | [Publisher Full Text](#)
4. Sundaram S, One J, Siewert J, et al.: **Tissue-engineered vascular grafts created from human induced pluripotent stem cells.** *Stem Cells Transl Med.* 2014; **3**(12): 1535–43.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
5. Fernandez CE, Yen RW, Perez SM, et al.: **Human Vascular Microphysiological System for in vitro Drug Screening.** *Sci Rep.* 2016; **6**: 21579.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
6. Zhang D, Shadrin IY, Lam J, et al.: **Tissue-engineered cardiac patch for advanced functional maturation of human ESC-derived cardiomyocytes.** *Biomaterials.* 2013; **34**(23): 5813–20.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
7. Duan B, Kapetanovic E, Hockaday LA, et al.: **Three-dimensional printed trileaflet valve conduits using biological hydrogels and human valve interstitial cells.** *Acta Biomater.* 2014; **10**(5): 1836–46.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
8. L'Heureux N, Dusserre N, Konig G, et al.: **Human tissue-engineered blood vessels for adult arterial revascularization.** *Nat Med.* 2006; **12**(3): 361–5.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
9. Sekine H, Shimizu T, Sakaguchi K, et al.: **In vitro fabrication of functional three-dimensional tissues with perfusable blood vessels.** *Nat Commun.* 2013; **4**: 1399.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
10. Feiner R, Engel L, Fleischer S, et al.: **Engineered hybrid cardiac patches with multifunctional electronics for online monitoring and regulation of tissue function.** *Nat Mater.* 2016.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
11. Weinberg CB, Bell E: **A blood vessel model constructed from collagen and cultured vascular cells.** *Science.* 1986; **231**(4736): 397–400.
[PubMed Abstract](#) | [Publisher Full Text](#)
12. Boccafroschi F, Rajan N, Habermehl J, et al.: **Preparation and characterization of a scaffold for vascular tissue engineering by direct-assembling of collagen and cells in a cylindrical geometry.** *Macromol Biosci.* 2007; **7**(5): 719–26.
[PubMed Abstract](#) | [Publisher Full Text](#)
13. Isenberg BC, Tranquillo RT: **Long-term cyclic distention enhances the mechanical properties of collagen-based media-equivalents.** *Ann Biomed Eng.* 2003; **31**(8): 937–49.
[PubMed Abstract](#) | [Publisher Full Text](#)
14. Syedain ZH, Meier LA, Bjork JW, et al.: **Implantable arterial grafts from human fibroblasts and fibrin using a multi-graft pulsed flow-stretch bioreactor with noninvasive strength monitoring.** *Biomaterials.* 2011; **32**(3): 714–22.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
15. Ghezzi CE, Risse PA, Marelli B, et al.: **An airway smooth muscle cell niche under physiological pulsatile flow culture using a tubular dense collagen construct.** *Biomaterials.* 2013; **34**(8): 1954–66.
[PubMed Abstract](#) | [Publisher Full Text](#)
16. Ghazanfari S, Driessen-Mol A, Sanders A, et al.: **In Vivo Collagen Remodeling in the Vascular Wall of Decellularized Stented Tissue-Engineered Heart Valves.** *Tissue Eng Part A.* 2015; **21**(15–16): 2206–15.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
17. Sarig U, Nguyen EB, Wang Y, et al.: **Pushing the envelope in tissue engineering: ex vivo production of thick vascularized cardiac extracellular matrix constructs.** *Tissue Eng Part A.* 2015; **21**(9–10): 1507–19.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
18. Dimitrievska S, Cai C, Weyers A, et al.: **Click-coated, heparinized, decellularized vascular grafts.** *Acta Biomater.* 2015; **13**: 177–87.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
19. Dahl SL, Kypson AP, Lawson JH, et al.: **Readily available tissue-engineered vascular grafts.** *Sci Transl Med.* 2011; **3**(68): 68ra9.
[PubMed Abstract](#) | [Publisher Full Text](#)
20. Weber B, Dijkman PE, Scherman J, et al.: **Off-the-shelf human decellularized tissue-engineered heart valves in a non-human primate model.** *Biomaterials.* 2013; **34**(30): 7269–80.
[PubMed Abstract](#) | [Publisher Full Text](#)
21. Weber M, Gonzalez de Torre I, Moreira R, et al.: **Multiple-Step Injection Molding for Fibrin-Based Tissue-Engineered Heart Valves.** *Tissue Eng Part C Methods.* 2015; **21**(8): 832–40.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
22. Wang RM, Christman KL: **Decellularized myocardial matrix hydrogels: In basic research and preclinical studies.** *Adv Drug Deliv Rev.* 2016; **96**: 77–82.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
23. Rothuizen TC, Damanik FF, Lavrijsen T, et al.: **Development and evaluation of in vivo tissue engineered blood vessels in a porcine model.** *Biomaterials.* 2016; **75**: 82–90.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
24. Bao X, Lian X, Dunn KK, et al.: **Chemically-defined albumin-free differentiation of human pluripotent stem cells to endothelial progenitor cells.** *Stem Cell Res.* 2015; **15**(1): 122–9.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
25. Patsch C, Challet-Meylan L, Thoma EC, et al.: **Generation of vascular endothelial and smooth muscle cells from human pluripotent stem cells.** *Nat*

- Cell Biol.* 2015; 17(8): 994–1003.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
26. Herberts CA, Kwa MS, Hermesen HP: Risk factors in the development of stem cell therapy. *J Transl Med.* 2011; 9: 29.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 27. Schlaeger TM, Daheron L, Brickler TR, *et al.*: A comparison of non-integrating reprogramming methods. *Nat Biotechnol.* 2015; 33(1): 58–63.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 28. Neofytou E, O'Brien CG, Couture LA, *et al.*: Hurdles to clinical translation of human induced pluripotent stem cells. *J Clin Invest.* 2015; 125(7): 2551–7.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 29. **F** Hou P, Li Y, Zhang X, *et al.*: Pluripotent stem cells induced from mouse somatic cells by small-molecule compounds. *Science.* 2013; 341(6146): 651–4.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
 30. Gieseck RL 3rd, Hannan NR, Bort R, *et al.*: Maturation of induced pluripotent stem cell derived hepatocytes by 3D-culture. *PLoS One.* 2014; 9(1): e86372.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 31. Zhang H, Xiong ZM, Cao K: Mechanisms controlling the smooth muscle cell death in progeria via down-regulation of poly(ADP-ribose) polymerase 1. *Proc Natl Acad Sci U S A.* 2014; 111(22): E2261–70.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 32. Lian X, Hsiao C, Wilson G, *et al.*: Robust cardiomyocyte differentiation from human pluripotent stem cells via temporal modulation of canonical Wnt signaling. *Proc Natl Acad Sci U S A.* 2012; 109(27): E1848–57.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 33. **F** Chen Y, Zeng D, Ding L, *et al.*: Three-dimensional poly(ϵ -caprolactone) nanofibrous scaffolds directly promote the cardiomyocyte differentiation of murine-induced pluripotent stem cells through Wnt/ β -catenin signaling. *BMC Cell Biol.* 2015; 16: 22.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 34. **F** Eng G, Lee BW, Protas L, *et al.*: Autonomous beating rate adaptation in human stem cell-derived cardiomyocytes. *Nat Commun.* 2016; 7: 10312.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 35. Christoforou N, Liao B, Chakraborty S, *et al.*: Induced pluripotent stem cell-derived cardiac progenitors differentiate to cardiomyocytes and form biosynthetic tissues. *PLoS One.* 2013; 8(6): e65963.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 36. **F** Riegler J, Tiburcy M, Ebert A, *et al.*: Human Engineered Heart Muscles Engraft and Survive Long Term in a Rodent Myocardial Infarction Model. *Circ Res.* 2015; 117(8): 720–30.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 37. **F** Monaghan MG, Holeiter M, Layland SL, *et al.*: Cardiomyocyte generation from somatic sources - current status and future directions. *Curr Opin Biotechnol.* 2016; 40: 49–55.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
 38. **F** Herron TJ, Rocha AM, Campbell KF, *et al.*: Extracellular Matrix-Mediated Maturation of Human Pluripotent Stem Cell-Derived Cardiac Monolayer Structure and Electrophysiological Function. *Circ Arrhythm Electrophysiol.* 2016; 9(4): pii: e003638.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 39. Mathur AB, Collinsworth AM, Reichert WM, *et al.*: Endothelial, cardiac muscle and skeletal muscle exhibit different viscous and elastic properties as determined by atomic force microscopy. *J Biomech.* 2001; 34(12): 1545–53.
[PubMed Abstract](#) | [Publisher Full Text](#)
 40. Godier-Furnémont AF, Tiburcy M, Wagner E, *et al.*: Physiologic force-frequency response in engineered heart muscle by electromechanical stimulation. *Biomaterials.* 2015; 60: 82–91.
[PubMed Abstract](#) | [Publisher Full Text](#)
 41. **F** Lippmann ES, Al-Ahmad A, Azarin SM, *et al.*: A retinoic acid-enhanced, multicellular human blood-brain barrier model derived from stem cell sources. *Sci Rep.* 2014; 4: 4160.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 42. Karakikes I, Ameen M, Termglinchan V, *et al.*: Human induced pluripotent stem cell-derived cardiomyocytes: insights into molecular, cellular, and functional phenotypes. *Circ Res.* 2015; 117(1): 80–8.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 43. **F** Wu H, Lee J, Vincent LG, *et al.*: Epigenetic Regulation of Phosphodiesterases 2A and 3A Underlies Compromised β -Adrenergic Signaling in an iPSC Model of Dilated Cardiomyopathy. *Cell Stem Cell.* 2015; 17(1): 89–100.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 44. Xie C, Hu J, Ma H, *et al.*: Three-dimensional growth of iPS cell-derived smooth muscle cells on nanofibrous scaffolds. *Biomaterials.* 2011; 32(19): 4369–75.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 45. **F** Wang Y, Hu J, Jiao J, *et al.*: Engineering vascular tissue with functional smooth muscle cells derived from human iPS cells and nanofibrous scaffolds. *Biomaterials.* 2014; 35(32): 8960–9.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 46. Bajpai VK, Mistrionis P, Loh YH, *et al.*: Functional vascular smooth muscle cells derived from human induced pluripotent stem cells via mesenchymal stem cell intermediates. *Cardiovasc Res.* 2012; 96(3): 391–400.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 47. Ji H, Atchison L, Chen Z, *et al.*: Transdifferentiation of human endothelial progenitors into smooth muscle cells. *Biomaterials.* 2016; 85: 180–94.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 48. Truskey GA, Yuan F, Katz DF: *Transport Phenomena in Biological Systems*. 2nd ed. Upper Saddle River: Pearson Prentice Hall; 2009.
[Reference Source](#)
 49. Peters EB, Christoforou N, Moore E, *et al.*: CD45+ Cells Present Within Mesenchymal Stem Cell Populations Affect Network Formation of Blood-Derived Endothelial Outgrowth Cells. *Biores Open Access.* 2015; 4(1): 75–88.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 50. Blocki A, Wang Y, Koch M, *et al.*: Not all MSCs can act as pericytes: functional *in vitro* assays to distinguish pericytes from other mesenchymal stem cells in angiogenesis. *Stem Cells Dev.* 2013; 22(17): 2347–55.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 51. **F** Kusuma S, Facklam A, Gerech S: Characterizing human pluripotent-stem-cell-derived vascular cells for tissue engineering applications. *Stem Cells Dev.* 2015; 24(4): 451–8.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 52. Cuchiara MP, Gould DJ, McHale MK, *et al.*: Integration of Self-Assembled Microvascular Networks with Microfabricated PEG-Based Hydrogels. *Adv Funct Mater.* 2012; 22(21): 4511–8.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 53. Alonzo LF, Moya ML, Shirure VS, *et al.*: Microfluidic device to control interstitial flow-mediated homotypic and heterotypic cellular communication. *Lab Chip.* 2015; 15(17): 3521–9.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 54. Ali S, Saik JE, Gould DJ, *et al.*: Immobilization of Cell-Adhesive Laminin Peptides in Degradable PEGDA Hydrogels Influences Endothelial Cell Tubulogenesis. *Biores Open Access.* 2013; 2(4): 241–9.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 55. **F** Hsu CW, Poché RA, Saik JE, *et al.*: Improved Angiogenesis in Response to Localized Delivery of Macrophage-Recruiting Molecules. *PLoS One.* 2015; 10(7): e0131643.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 56. Park KM, Gerech S: Harnessing developmental processes for vascular engineering and regeneration. *Development.* 2014; 141(14): 2760–9.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 57. Chan XY, Black R, Dickerman K, *et al.*: Three-Dimensional Vascular Network Assembly From Diabetic Patient-Derived Induced Pluripotent Stem Cells. *Arterioscler Thromb Vasc Biol.* 2015; 35(12): 2677–85.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 58. Baranski JD, Chaturvedi RR, Stevens KR, *et al.*: Geometric control of vascular networks to enhance engineered tissue integration and function. *Proc Natl Acad Sci U S A.* 2013; 110(19): 7586–91.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 59. **F** Chaturvedi RR, Stevens KR, Solorzano RD, *et al.*: Patterning vascular networks *in vivo* for tissue engineering applications. *Tissue Eng Part C Methods.* 2015; 21(5): 509–17.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 60. **F** Mathur A, Loskill P, Shao K, *et al.*: Human iPSC-based cardiac microphysiological system for drug screening applications. *Sci Rep.* 2015; 5: 8883.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 61. **F** Ligresti G, Nagao RJ, Xue J, *et al.*: A Novel Three-Dimensional Human Peritubular Microvascular System. *J Am Soc Nephrol.* 2015; pii: ASN.2015070747.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
 62. **F** Zachos NC, Kovbasnjuk O, Foulke-Abel J, *et al.*: Human Enteroids/Colonoids and Intestinal Organoids Functionally Recapitulate Normal Intestinal Physiology and Pathophysiology. *J Biol Chem.* 2016; 291(8): 3759–66.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 63. **F** Benam KH, Villenave R, Lucchesi C, *et al.*: Small airway-on-a-chip enables analysis of human lung inflammation and drug responses *in vitro*. *Nat Methods.* 2016; 13(2): 151–7.
[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)
 64. **F** Vernetti LA, Senutovitch N, Boltz R, *et al.*: A human liver microphysiology platform for investigating physiology, drug safety, and disease models. *Exp Biol Med (Maywood).* 2016; 241(1): 101–14.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 65. Madden L, Juhas M, Kraus WE, *et al.*: Bioengineered human myobundles mimic clinical responses of skeletal muscle to drugs. *eLife.* 2015; 4: e04885.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)
 66. **F** Arslan SY, Yu Y, Burdette JE, *et al.*: Novel three dimensional human endocervix cultures respond to 28-day hormone treatment. *Endocrinology.* 2015; 156(4): 1602–9.
[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)
 67. **F** Zhang J, Lian Q, Zhu G, *et al.*: A human iPSC model of Hutchinson Gilford

Progeria reveals vascular smooth muscle and mesenchymal stem cell defects. *Cell Stem Cell*. 2011; **8**(1): 31–45.

[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)

68. Biel NM, Santostefano KE, DiVita BB, *et al.*: **Vascular Smooth Muscle Cells From Hypertensive Patient-Derived Induced Pluripotent Stem Cells to Advance Hypertension Pharmacogenomics.** *Stem Cells Transl Med*. 2015; **4**(12): 1380–90.

[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)

69. Santostefano KE, Hamazaki T, Biel NM, *et al.*: **A practical guide to induced pluripotent stem cell research using patient samples.** *Lab Invest*. 2015; **95**(1): 4–13.

[PubMed Abstract](#) | [Publisher Full Text](#) | [F1000 Recommendation](#)

70. Blum A, Shamburek R: **The pleiotropic effects of statins on endothelial function, vascular inflammation, immunomodulation and thrombogenesis.** *Atherosclerosis*. 2009; **203**(2): 325–30.

[PubMed Abstract](#) | [Publisher Full Text](#)

71. Agarwal A, Goss JA, Cho A, *et al.*: **Microfluidic heart on a chip for higher throughput pharmacological studies.** *Lab Chip*. 2013; **13**(18): 3599–608.

[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#)

72. Wang G, McCain ML, Yang L, *et al.*: **Modeling the mitochondrial cardiomyopathy of Barth syndrome with induced pluripotent stem cell and heart-on-chip technologies.** *Nat Med*. 2014; **20**(6): 616–23.

[PubMed Abstract](#) | [Publisher Full Text](#) | [Free Full Text](#) | [F1000 Recommendation](#)

Open Peer Review

Current Peer Review Status:

Editorial Note on the Review Process

Faculty Reviews are review articles written by the prestigious Members of **Faculty Opinions**. The articles are commissioned and peer reviewed before publication to ensure that the final, published version is comprehensive and accessible. The reviewers who approved the final version are listed with their names and affiliations.

The reviewers who approved this article are:

Version 1

1. **Irving H Zucker**

Department of Cellular and Integrative Physiology, University of Nebraska Medical Center, Omaha, NE, 68198, USA

Competing Interests: No competing interests were disclosed.

2. **Gordana Vunjak-Novakovic**

Departments of Biomedical Engineering and Medicine, Columbia University, New York, NY, USA

Competing Interests: No competing interests were disclosed.

3. **David Schaffer**

Department of Bioengineering, Department of Chemical and Biomolecular Engineering and Department of Molecular and Cell Biology, University of California, Berkeley, Berkeley, CA, 94720-3220, USA

Competing Interests: No competing interests were disclosed.

The benefits of publishing with F1000Research:

- Your article is published within days, with no editorial bias
- You can publish traditional articles, null/negative results, case reports, data notes and more
- The peer review process is transparent and collaborative
- Your article is indexed in PubMed after passing peer review
- Dedicated customer support at every stage

For pre-submission enquiries, contact research@f1000.com

F1000Research